

Arnitel[®] ECO L400

TPC

>50% Renewable Content, Food Contact Quality

Print Date: 2024-09-17

Sustainability

Bio-based

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES		VALUE	
Melt volume-flow rate	45	cm³/10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (parallel)	1.2	%	ISO 294-4
Molding shrinkage (normal)	1.2	%	ISO 294-4
MECHANICAL PROPERTIES		VALUE	
Shore D Hardness (3s)	34	—	ISO 868
Tensile modulus	40	MPa	ISO 527-1/-2
Stress at break	9	MPa	ISO 527-1/-2
Nominal strain at break	200	%	ISO 527-1/-2
Stress at 5% strain	2.7	MPa	ISO 527-1/-2
Stress at 10% strain	4.5	MPa	ISO 527-1/-2
Stress at 50% strain	7.7	MPa	ISO 527-1/-2
Stress at 100% strain	8.3	MPa	ISO 527-1/-2
Tear strength	75	kN/m	ISO 34-1; Method B
Compression Set under constant strain at 70 °C	47	%	ISO 815
THERMAL PROPERTIES		VALUE	

All the trademarks mentioned here are trademarks of Envalior.
Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Arnitel[®] ECO L400

Print Date: 2024-09-17

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Melting temperature (10°C/min)	158	°C	ISO 11357-1/-3
ELECTRICAL PROPERTIES	VALUE		
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	20	kV/mm	IEC 60243-1
OTHER PROPERTIES	VALUE		
Density	1100	kg/m³	ISO 1183
Humidity absorption	0.04	%	Sim. to ISO 62

All the trademarks mentioned here are trademarks of Envalior.
Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.